

**TEST REPORT**

Applicant : Shijiazhuang Gonghao Textile Co., Ltd.

Date : Oct 24, 2011

Attn : Catherine Gai

## Sample Description:

One (1) Piece Of Submitted Baby Cloth Diaper, Snap At Face, In Lt.Yellow For Baby'S.

## Chemical Test Component As Follows:

- (1) White Cap Of Snap For Sample Use,
- (2) Lt.Yellow Face Knitted Fabric With Coating For Sample Use,
- (3) Grey Fleece Lining Fabric For Sample Use.

Date Received : 10/18/2011

Date Tests Started : 10/18/2011


## Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

## Conclusion:

<u>Tested Components</u>	<u>Standard</u>	<u>Result</u>
(1)(2)&(3)	U.S. Consumer Product Safety Improvement Act 2008 (Public Law 110-314)Title I, Section 108 & Amendment H.R. 2715 For Phthalate Content	Pass
(1)	U.S. Consumer Product Safety Improvement Act 2008 Title I, Section 101 For Total Lead Content In Non-Surface Coating Materials (Substrate)	Pass

Authorized By :  
For Intertek Testing Services  
(Tianjin) Ltd.



Alex Wang  
General Manager



NUMBER : TSNT00390504

### TEST REPORT

Tests Conducted:

1. Phthalate Content Test On Tested Components

With Reference To CPSC-CH-C1001-09.3 , By Gas Chromatographic-Mass Spectrometric (GC-MS) Analysis.

	Result (% , W/W)			Limit (% , W/W) (Max.)
	(1)	(2)	(3)	
Dibutyl Phthalate (DBP)	ND	ND	ND	0.1
Diethyl Hexyl Phthalate (DEHP)	ND	ND	ND	0.1
Benzyl Butyl Phthalate (BBP)	ND	ND	ND	0.1
Di-Iso-Nonyl Phthalate (DINP)	ND	ND	ND	0.1
Di-N-Octyl Phthalate (DNOP)	ND	ND	ND	0.1
Di-Iso-Decyl Phthalate (DIDP)	ND	ND	ND	0.1

Remark : The Above Limit Was Quoted According To Us Consumer Product Safety Improvement Act 2008(Public Law 110-314) & Amendment H.R. 2715 For Prohibition On Sale Of Certain Products Containing Specified Phthalates.

Detection Limit = 0.01% (W/W)  
ND = Not Detected

2. Total Lead (Pb) Content In Non-Surface Coating Materials (Substrate) :

As Per Standard Operating Procedures For Determining Total Lead (Pb) In Children's Products, Test Method CPSC-CH-E1002-08 Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

<u>Tested Component</u>	<u>Result In ppm</u>	<u>Requirement In ppm</u>
(1)	<10	100

Remark : ppm = parts per million  
< = Less Than